



Chemical Resistance Guide- 6.0 HP Epoxy

RATINGS KEY

E = Excellent NR = Not Recommended
 G = Good OS = Occasional Spillage
 F = Fair

ORGANIC ACIDS

REAGENT	CONC.	RATING	
		CLEAR	w/Pigment
Acetic	5%	E	E
Acetic	10%	E	E
Acetic	20%	G	E
Acetic	Glacial	F	F
Butyric	10%	F	E
Citric	10%	F	F
Citric	50%	F	NR
Cresylic	10%	F	G
Formic	10%	E	E
Lactic	10%	G	G
Lactic	25%	F	G
Maleic	30%	F	F
Maleic	60%	F	F
Malic	50%	F	F
Monochloro Acetic	5%	F	G
Monochloro Acetic	10%	F	F
Oleic	Sat.	E	E
Oxalic	Sat.	E	E
Picric	Sat.	E	G

INORGANIC ACIDS

REAGENT	CONC.	RATING	
		CLEAR	w/Pigment
Boric	30%	G	G
Boric	Sat.	G	G
Chromic Acid	2%	E	F
Chromic Acid	10%	E	F
Chromic Acid	15%	G	G
Hydrochloric	10%	G	F
Hydrochloric	37%	F	F
Hydrochloric	Conc.	G	F
Hydrofluoric	10%	E	G
Hydrofluoric	24%	G	G
Hypochlorous	5%	G	G
Nitric	10%	G	G
Nitric	30%	G	NR
Nitric Over	40%	G	NR
Nitric	Conc.	NR	NR
Perchloric	35%	F	G
Phosphoric	10%	G	F
Phosphoric	35%	G	F
Phosphoric	75%	F	F
Sulfuric	25%	F	G
Sulfuric	50%	F	F
Sulfuric	70%	OS	F
Sulfuric	Conc.	NR	NR

KETONES - ESTERS

REAGENT	CONC.	RATING	
		CLEAR	w/Pigment
Acetone	100%	G	F
Amyl Acetate	100%	E	E
Butyl Acetate	100%	G	G
Ethyl Acetate	100%	G	F
Methyl Ethyl Ketone	100%	G	G
Methyl Isobutyl Ketone	100%	NR	NR
PM Acetate	100%	E	F

ALKALIES AND SALTS

REAGENT	CONC.	RATING	
		CLEAR	w/Pigment
Aluminum Chloride		50%	E E
Ammonium Chloride	50%	E	E
Ammonium Hydroxide	10%	E	E
Ammonium Hydroxide	20%	E	E
Ammonium Hydroxide	50%	E	E
Ammonium Nitrate	Sat.	E	E
Ammonium Persulfate	Sat.	E	E
Ammonium Sulfate	Sat.	E	E
Calcium Chloride	50%	G	G
Calcium Hydroxide	Sat.	E	E
Calcium Hypochlorite	15%	F	F
Ferric Chloride	Sat.	E	E
Ferric Sulfate	Sat.	G	G
Potassium Hydroxide	40%	F	F
Sodium Bicarbonate	Sat.	E	E
Sodium Bisulfate	Sat.	E	E
Sodium Carbonate	Sat.	E	E
Sodium Chloride	20%	E	E
Sodium Hydroxide	10%	E	E
Sodium Hydroxide	50%	E	E
Sodium Hypochlorite	10%	E	E
Sodium Sulfate	Sat.	E	E
Sodium Sulfide	Sat.	E	E
Trisodium Phosphate	10%	E	E
Trisodium Phosphate	Sat.	E	E

SOLVENTS - ALIPHATIC

REAGENT	CONC.	RATING	
		CLEAR	w/Pigment
Gasoline	100%	E	E
Hexane	100%	E	E
Jet Fuel A-1	100%	E	E
Mineral Spirits	100%	E	E
Naphtha	100%	E	E



Chemical Resistance Guide- 6.0 HP Epoxy

SOLVENTS - AROMATIC

REAGENT	CONC.	RATING	
		CLEAR	w/Pigment
Benzene	100%	F	F
Chlorobenzene	100%	G	G
SC-100	100%	E	E
Toluene	100%	E	F
Xylene	100%	E	E

SOLVENTS - CHLORINATED

REAGENT	CONC.	RATING	
		CLEAR	w/Pigment
Methylene Chloride	100%	F	G
Perchloroethane	100%	E	E
1,1,1, Trichloroethane	100%	E	E
Trichloroethylene	100%	G	G

AUTO-BRAKE - HYDRAULIC FLUIDS

REAGENT	CONC.	RATING	
		CLEAR	w/Pigment
Brake Fluid	100%	F	F
Hy-Jet Fuel #3	100%	F	F
Motor Oil	100%	E	E
Skydrol 500A	100%	F	F
Skydrol 500B	100%	F	F
Transmission Fluid	100%	E	F

ALCOHOLS

REAGENT	CONC.	RATING	
		CLEAR	w/Pigment
Diacetone Alcohol	100%	G	E
Ethyl Alcohol	100%	F	F
Ethylene Glycol	100%	E	E
Glycerine	100%	E	E
Isopropyl Alcohol	100%	G	F
Methyl Alcohol	100%	G	G
Phenol	5%	NR	NR
Triethylene Glycol	100%	G	G

MISCELLANEOUS CHEMICALS

REAGENT	CONC.	RATING	
		CLEAR	w/Pigment
Acrylonitrile	100%	G	G
Aniline	100%	NR	NR
Beer	100%	E	E
Bromine	100%	NR	NR
Butyl Lactate	100%	G	G
Carbon Disulfide	100%	F	F
Carbon Tetrachloride	100%	G	G
Chloroform	100%	G	G
Cola	100%	E	E
Corn Oil	100%	E	E
Cyclohexane	100%	G	G
Cyclohexanone	100%	G	G
Diethyl Phthalate	100%	G	G
Dimethyl Phthalate	100%	G	G
Ethylene Dichloride	100%	F	G
Formaldehyde	100%	F	G
Fruit Juice	100%	E	F
Grease	100%	E	E
Hydrogen Peroxide	10%	E	G
Ketchup	100%	E	G
Lanoline	100%	E	E
Lard	100%	E	E
Linseed Oil	100%	E	E
Mayonnaise	100%	E	E
Methyl Salicylate (50% in Toluene)		NR	NR
Milk	100%	E	E
Mustard	100%	F	F
2-Nitro-Propane	100%	E	G
Pyridine	100%	NR	F
Sugar	Sat.	E	E
Tannic Acid	Sat.	E	G
Tartaric Acid	Sat.	G	G
Tide Solution	2%	E	E
Triacetin	100%	E	E
Triethanolamine	100%	E	E
Turpentine	100%	E	E
Water	100%	E	E
Wine	100%	E	E

October 2013

WARRANTY STATEMENT | IMPORTANT: The data on this sheet represent typical values, and since application variables are a major factor in product performance, this information should serve only as a general guide.

Xtreme Engineered Floor Systems assumes no obligation or liability for use of this information.